

SIRIO PEARL

Papers and boards certify FSC, made with E.C.F. pulp, treated on both sides with a pearlescent finish. Pulp-dyed with light-fast colours carbon black free. In the substance 110 gsm the pearlescent finish is only on one side. It's available in sixteen colours.

DESCRIPTION

SIZE	GRAIN	SUBSTANCE
70X100	LG	480 700
72X102	LG	110 125 230 300 350

RANGE

SUBSTANCE	VSA	TABER STIFFNESS 15°		TENSILE STRENGTH	
ISO 536	ISO 534	ISO 2493		ISO 1924	
g/m ²	cm ³ /g	mN		kN/m	
		long ± 10%	cross ± 10%	long ± 10%	cross ± 10%
110 ± 3%	1,2	13	6	7,8	4,5
125 ± 3%	1,2	25	12	8,5	5,2
230 ± 4%	1,2	110	50	13,7	7,8
300 ± 5%	1,15	230	110	17,6	10,4
350 ± 5%	1,15	350	150	-	-
480 ± 5%	1,15	1100	650	-	-
700 ± 5%	1,15	3000	1700	-	-

TECHNICAL FEATURES

ref. standard/instrument
unit of measure

Relative Humidity 50% ± 5
ref. TAPPI 502-98



ECOLOGICAL FEATURES

The suggestions given on the next page come from research carried out with a number of printers that have used Sirio Pearl very satisfactorily. This is supported by R&D with ink manufacturers and finishing equipment suppliers. The product is completely bio-degradable and recyclable. Special runs available upon request.

NOTES

Envelopes available on stock.

SIRIO PEARL

Sirio Pearl is a collection of papers and boards that are suitable for many applications. It is excellent for publications, packaging, corporate literature, labels, covers, inserts and brochures - wherever the need is to show a technical emphasis, a modern style and futuristic design.

APPLICATIONS

Can be used with the main printing systems: letterpress, offset, blind embossing, hot-foil stamping, thermographic and screen printing. The surface has no porosity, so that inks do not dry through absorption into the media. Polymerisation in offset printing from the sheet takes place by means of oxidation, so that inks for plastics should be used. Excellent results have been achieved with U.V. inks and in web offset printing with Heat Set inks. The anchorage of the ink, once dry, is very good. It is also particularly important to check the other process variables, especially the fountain solution, which must be dosed at minimum levels to ensure that emulsifying is kept within modest levels. We recommend a buffered pH of 5÷5,5 with 800÷1200 µS conductivity. It may be appropriate to add small quantities of additives to the fountain solution and/or the ink to accelerate the ink polymerisation process. Anti-setoff spray powder is useful and low output stacks are necessary; we advise against the use of varnish online if used to avoid setoff. Drying times depend on the quantity of ink and process variables and may vary from 8-10 hours to more than 24 hours. In this regard, good results are obtained with UCR and GCR grading to reduce the mass of ink deposited on the paper. In screen-printing, and even hot foil stamping, we recommend inks for plastic-finished surfaces.

PRINTING SUGGESTIONS

Good results can be expected with all the main converting process: cutting, die cutting, scoring, folding, glueing, varnishing and lamination. The surface roughness typical of these papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate. For the correct choice of adhesive, it is advisable to carry out specific testing with the supplier.

CONVERTING SUGGESTIONS

